



# COBALT-Z DRIER

# 1873

Drier Solution for Solvent Base Systems

HMS CODE:	
HEALTH: 2	FLAMMABILITY: 2
REACTIVITY: 0	PERSONAL PROTECTION: B

## PRODUCT DATA

### AVAILABLE IN:

**BASES:** N/A

**COLORS:** N/A

### RECOMMENDED PRIMERS:

**DESCRIPTION:** 1873 Cobalt-Z Drier is a drier solution additive to PARKER PAINT'S interior and exterior alkyd oil, oil base paint and most solvent thinned varnishes to help accelerate and promote faster drying properties.

The addition of one to two fluid ounces per gallon of paint or varnish is sufficient. Excessive amounts may cause discoloration and a slower curing time of the coating.

### APPLICATION:

Mix paint thoroughly before using.

### RECOMMENDED DRY FILM THICKNESS

**PER COAT:** N/A

**WET FILM TO ACHIEVE DFT:** N/A

(Unthinned Material)

### THEORETICAL COVERAGE

**AT RECOMMENDED DFT:** N/A

**NOT RECOMMENDED FOR:** Latex paints, shellacs, lacquers or epoxies and urethanes.

**NOT FOR USE WITH PRODUCTS OTHER THAN PARKER PAINT PRODUCTS.**

### RECOMMENDED APPLICATION

#### TEMPERATURES AND HUMIDITY:

50 - 90° F (10 - 32° C) 50 - 55% RH

**DRYING TIMES:** TACK FREE: N/A

@ 70 - 80° F RECOAT: N/A

and 50% RH DRY HARD: N/A

**NOTE:** See back under Precautionary Information.

**SURFACE PREPARATION:** N/A

### EQUIPMENT RECOMMENDATIONS:

**BRUSH:** N/A

**AIR ATOMIZED SPRAY:** N/A

**AIRLESS SPRAY:** N/A

**THINNING:** N/A

### RECOMMENDED THINNERS FOR

#### APPLICATING EQUIPMENT:

**BRUSH:** N/A

**AIR ATOMIZED SPRAY:** N/A

**AIRLESS SPRAY:** N/A

**CLEAN-UP:** Clean all tools and equipment immediately after use with clean paint thinner.

**PRODUCT ANALYSIS:** 1873  
**PIGMENT:** \_\_\_\_\_ N/A

**VEHICLE:** \_\_\_\_\_ N/A

**VEHICLE TYPE:** Cobalt and Zirconium

**SOLVENT TYPE:** Naphthenates in Mineral Spirits

**VOC GRMS/L:** 690 g/l 5.76 lbs./gal.

**APPEARANCE:** Clear

**GLOSS RANGE:** N/A

**VISCOSITY:** Very thin  
(@ 77° F [25° C])

**% SOLIDS BY WEIGHT:** N/A

**% SOLIDS BY VOLUME:** N/A

**WEIGHT/GAL:** 7.1

**PACKAGING:** FIVE: ONE: X QT:

**SHELF LIFE:** N/A

**TINTING:** N/A

**PRECAUTIONARY INFORMATION:**  
**CLOSE CONTAINER AFTER EACH USE**

**KEEP OUT OF REACH OF CHILDREN**

**DO NOT TAKE INTERNALLY**

**OMBUSTIBLE**

**FLASH POINT:** 105° (Set-A-Flash)

**D.O.T. (REQUIREMENTS):** N/A

**STORE** in a clean dry place away from high heat and open flame. Vapors may ignite.

**RECOMMENDED STORAGE TEMPERATURES**  
should be between 38 - 100° F (3 - 38° C)

**EXTINGUISHING MEDIA:** CO<sub>2</sub>, Dry Chemical, Alcohol Foam.

**USE WITH ADEQUATE VENTILATION.** Avoid prolonged or repeated contact with skin and breathing vapors or spray mist. Coatings should only be applied when ventilation is adequate. If there is not adequate ventilation, applicators should wear respirator approved by NIOSH / MSHA (TC-23C or equivalent).

**THINNER - CAUTION:**

CONTAINS: MINERAL SPIRITS

Keep away from heat, sparks and flame. Avoid breathing of vapor or spray mist. Avoid contact with eyes and skin. Keep container closed when not in use. Keep closures tight and upright to prevent leakage. In case of spoilage, absorb and dispose of in accordance with local applicable regulations.

**FIRST AID**

In case of skin contact, flush with plenty of water; for eyes, immediately flush with plenty of water for 15 minutes and get medical attention. If you experience eye watering, headaches or dizziness, increase fresh air or wear respiratory protection (NIOSH/MSHA TC 23C or equivalent) or leave the area. If swallowed, CALL A PHYSICIAN IMMEDIATELY.

**NOTICE**

Reports have associated repeated and prolonged occupational over-exposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.

**ENVIRONMENTAL CONSIDERATIONS**  
**Formulated without lead or mercury.**

**MATERIAL SAFETY DATA SHEET AVAILABLE ON REQUEST**

**REVISED:** 2/99 (Supercedes 12/96)

To the best of our knowledge, the information presented herein is correct. No guarantee of accuracy is given or implied. The information is subject to change without prior notice. Because conditions of surface preparation, material handling, and application are beyond our control, we assume no responsibility for product performance or injuries resulting from use of our products. Liability, if any is limited to the replacement of products. No other warranty or guarantee of any kind is made by the seller, express or implied, statutory, by operation or law or otherwise, including merchantability and fitness for a particular purpose.