



COLD COAT 34

150

Exterior Acrylic Flat Latex PRODUCT DATA

HMIS CODE:
HEALTH: 1 FLAMMABILITY: 0
REACTIVITY: 0 PERSONAL PROTECTION: B

AVAILABLE IN:

BASES: 150 White
105 Medium Base

COLORS:

DESCRIPTION: PARKER PAINT's 150 is an exterior 100% acrylic latex, formulated to produce a durable flat finish with excellent weathering, flexibility and color retention that can be applied when the air and surface temperatures are at or above 34°F (1.1°C). The surface temperatures should be checked prior to painting to be sure it is above 34°F (1.1°C). The surface temperature can affect the drying time of the coating. Ease of application and clean up makes it an excellent product for the homeowner or painting contractor. Can be used on properly prepared new structures or recoating previously painted surfaces, such as smooth and rough wood siding, trim and sash, shakes and shingles, T111 and 303 type plywood, concrete, masonry and stucco.

DO NOT USE: Over bare metal, and particle board. These surfaces need special painting procedures and special primers. Ask any Parker Paint representative for instructions about painting these surfaces.

SURFACE PREPARATION: Before applying, read and follow all directions and cautions on container label.

All surfaces to be coated, old and new, must be sound, clean, dry and free of dirt, dust, sawdust, chalk, mildew, oils, efflorescence, blistering or peeling paint, organic matter or any other contamination that can affect the paint film. This can be achieved by wire brushing, scraping, pressure washing, acid etching, grit blasting or any other allowable means for removing surface contaminants.

New wood, concrete and/or masonry type substrates should have a moisture content not exceeding 15%, as determined by a moisture meter. The meter probe must be 1/4 inch below the substrate surface of the concrete and/or masonry. Some coatings may require a moisture content reading well below this amount. New concrete, masonry and stucco must be allowed to dry and cure for a minimum of 30 days, prior to painting.

If high pressure water cleaning is used to remove flaking or peeling paint, or for washing the house or structure, it should be let to dry for one week in good weather before priming and/or painting. The moisture content of the substrate should not exceed 15%, as determined by a moisture meter. Clean and fill all major cracks, voids, nail and staple holes. Repair any moisture problems.

Mold and mildew can be removed by washing with a solution of 6 - 8 ounces of a non-phosphate detergent, 1 quart bleach in 1 gallon hot water. Let set 15 to 20 minutes after applying solution, then rinse thoroughly with fresh water. Shrubbery and plants should be watered down and covered before and after applying solution. Wear protective eye shields and clothing while using this solution. Let substrate dry thoroughly before priming and/or applying finish coating.

Caution should be taken if a flammable product is used for cleaning. For specialized painting and/or cleaning procedures, ask your PARKER PAINT representative for additional instructions.

RECOMMENDED PRIMERS:

WOOD: 450 First Kote
2333 Flex Prime
1875 Cold Coat 34 Primer

MASONRY/CONCRETE AND STUCCO:
2345 Flex Bind 1875 Cold Coat 34 Primer
2333 Flex Prime 2347 Latex Block Filler
1840 Alkali Resistant Primer

NEW GALVANIZED & ALUMINUM:
1821 Galv O Prime

METAL:
1651 Zinc Phosphate Alkyd
1652 Rust Proof Red Alkyd
1655 White Metal Primer Alkyd
1679 Overlay Red Primer Alkyd

PVC/PLASTIC: 1640 Overlay White Primer
2333 Flex Prime

PRE-PRIMED METAL: 1640 Overlay White Primer
1875 Cold Coat 34 Primer
2333 Flex Prime

APPLICATION:

Mix paint thoroughly before using.

RECOMMENDED DRY FILM THICKNESS

PER COAT: 1.5 mils.

WET FILM TO ACHIEVE DFT: 4.4 mils.

(Unthinned Material)

THEORETICAL COVERAGE

AT RECOMMENDED DFT: 300 - 350 sq. ft. per/gal

Coverage will depend upon the method of application, porosity and texture of the surface.

Do not apply exterior paint coatings during rain or in damp, foggy or freezing weather. Any one or all of these conditions can affect the drying, appearance and durability of a paint coating.

Must be applied thick enough to thoroughly coat the surface. In some cases, a second coat may be required.

Do not apply to a hot surface or in the direct sunlight. One or both could cause the paint coating to blister and/or peel.

Apply a coating of paint only when the air, product and surface temperatures are at or above 34°F (1.1°C).

RECOMMENDED APPLICATION

TEMPERATURES AND HUMIDITY:

34°F - 60°F (1.1°C - 16°C) 50% RH

DRYING TIMES: TACK FREE: 1 hour

@ 77°F (25°C) RECOAT: 4 - 6 hours

50 - 55 RH DRYHARD: 24 hours

NOTE: See back under Precautionary Information.

EQUIPMENT RECOMMENDATIONS:

BRUSH/ROLLER: Use premium quality nylon or polyester brushes and roller covers, (1/2" nap minimum recommended.). To insure a uniform finish and avoid lap marks, maintain a wet edge and apply with a fully loaded brush or roller cover.

AIR ATOMIZED SPRAY: With a suitable nozzle set up.

AIRLESS SPRAY: With tip size of .015 to .021.

THINNING: No thinning is necessary. If necessary, add no more than 4 fl. oz. clean water per gallon. Do not add any type of oil additive to this product.

CLEAN-UP: Clean all tools and equipment immediately after use with clean water. Rinse with clean water.

Keep containers closed when leaving the work area!

PRODUCT ANALYSIS: 150 Exterior Latex Cold Coat 34

PIGMENT:		35%
Titanium Dioxide	53%	
Silicates	40%	
Amorphous Silica	7%	
	100%	

VEHICLE:		65%
Acrylic Emulsion	36%	
Isopropyl Alcohol	5%	
Water & Additives	59%	
	100%	100%

VEHICLE TYPE: Acrylic

SOLVENT TYPE: Water

VOC GRMS/L: 114 grams/lite .95lbs./gal.

APPEARANCE: Flat

GLOSS RANGE: 2 - 5 @ 60° 2 - 5 @ 85°

VISCOSITY: 95 -1 00 KU's (@ 77° F [25° C])

% SOLIDS BY WEIGHT: 50.4% plus/minus 1.5%

% SOLIDS BY VOLUME: 34% plus/minus 1.5%

WEIGHT/GAL: 10.8 - 11.0 lbs./gal.

PACKAGING: FIVE: X ONE: X QT:

SHELF LIFE: N/A

TINTING: PARKER PAINT Color Guild Colorants.
Custom mix colors may not dry to an exact match to the sample chip. Apply the paint to a small test area.
APPLICATION OF A COLOR COULD CONSTITUTE ACCEPTANCE OF THE COLOR.
PARKER PAINT assumes no responsibility expressed or implied for mismatched colors after it has been applied. No refunds on custom mixed colors unless the company is in error.

ENVIRONMENTAL CONSIDERATIONS Formulated without lead or mercury.
--

PRECAUTIONARY INFORMATION:
CLOSE CONTAINER AFTER EACH USE

KEEP OUT OF REACH OF CHILDREN

DO NOT TAKE INTERNALLY

FLASH POINT: 204°F

D.O.T. (REQUIREMENTS): N/A

STORE in a clean, dry place.

RECOMMENDED STORAGE TEMPERATURES
should be between: 40 - 100° F (5° - 38° C)

KEEP FROM FREEZING

EXTINGUISHING MEDIA: Water may be used to cool closed containers to prevent pressure build-up and explosion when exposed to extreme heat.

NOTE: Avoid any exterior application of a latex paint late in the afternoon, when dew condensation is likely to form, or if rain is threatening. Dry times will vary depending upon substrate and air temperature, air circulation or ventilation. Do not apply if the surface or air temperature is or soon will be below 34°F or above 60°F, or in direct sunlight to a hot surface. Any one or all of these conditions can affect the drying, appearance and durability of a paint coating.

SPECIAL NOTE: "Surfactant Bleed"; sticky white, brown or clear runs or spots can occur on newly painted surfaces if exposed to moist conditions before surfactants can evaporate from the drying paint film.

Cedar, redwood, fir plywood and many other wood by products contain a soluble extractive which can discolor white or light colored latex and oil base coatings. This extractive staining can develop months after the finish is applied. It is recommended that a primer, specifically formulated to retard this discoloration, be used first. There is no guarantee that one coat of either a latex or oil base primer will prevent EXCESSIVE extractive bleeding. Do not apply a paint coating to a hot surface or in the direct sunlight. One or both could cause the coating to blister and/or peel.

This product has been formulated to resist mildew growth on dried paint film. There are no known methods or chemicals to eliminate the growth of mildew if the conditions are favorable to its growth; therefore Parker Paint Company assumes no responsibility for mildew development.

USE WITH ADEQUATE VENTILATION. Avoid prolonged or repeated contact with skin and breathing of vapors or spray mist. Coatings should only be applied when ventilation is adequate. If there is not adequate ventilation, applicators should wear respirator protection approved by NIOSH / MSHA (TC-23C or equivalent).

MATERIAL SAFETY DATA SHEET AVAILABLE ON REQUEST

REVISED: 1/99 (Supersedes 3/97)

To the best of our knowledge, the information presented herein is correct. No guarantee of accuracy is given or implied. The information is subject to change without prior notice. Because conditions of surface preparation, material handling, and application are beyond our control, we assume no responsibility for product performance or injuries resulting from use of our products. Liability, if any is limited to the replacement of products. No other warranty or guarantee of any kind is made by the seller, express or implied, statutory, by operation or law or otherwise, including merchantability and fitness for a particular purpose.